

About

The anatomically shaped 600mm (24") BioClean Maxima Sterile Latex Glove provide shoulder length protection and are flexible and comfortable enabling prolonged use. The natural-coloured, glove features a textured surface, are double-donnable and have a beaded cuff for strength.

BIOCLEAN MAXIMA Sterile Latex Gloves BLLS

SHOULDER LENGTH

ANATOMICALLY SHAPED

of cleanroom gloves

DOUBLE-DONNABLE

Specifications

COMPATIBILITY:

ISO Class 4 & EU GMP Grade A

LENGTH:

600mm (24")

MATERIAL:

Latex

PROTEIN LEVEL:

Less than 50µg/gram

SURFACE:

Textured

SHAPE:

Hand specific

COLOUR:

Natural

STERILIZATION:

Gamma irradiation

Features

- Flexible & comfortable
- Shoulder length protection
- Powder-free
- · Beaded cuff
- Easy double-donning
- Non-particulating EasyTear packaging

EN 421:2010 ISO 374-5:2016















Quality Standards

- Manufactured in a facility holding ISO 9001:2015 and (EU)2016/425
 Module D certifications
- Conforms to Category 3 Complex Design Personal Protective Equipment PPE Regulation (EU)2016/425
- Processed in an NEBB certified ISO Class 4 environment
- Complies with the requirements of European Glove Standards EN420:2003 +A1:2009, EN374-1:2016, EN374-5:2016 and EN421:2010
- Physical properties comply with European Medical Glove Standard EN455-2:2015
- Sterilized in accordance with ISO 11137-1:2006
- Suitable for contact with all foodstuffs. Regulation (EC)1935/2004 and (EC) 2023/2006.

Physical Properties

CHARACTERISTICS	VALUE	TEST METHOD
Freedom From Holes	1.5 AQL Performance Level 2	EN 374-2:2015
Glove Length +/-10mm (mm/inches)	580/22.8	EN 420:2003 + A1:2009
Single Wall Thickness Minimum (mils/mm)	Cuff: 4.72/0.12 Palm: 7.09/0.18 Finger Tip: 7.87/0.20	EN 455-2:2015
Force At Break During Shelf Life	≥ 9 N	EN 455-2:2015

PALM WIDTHS (mm) ± 5mm								
SIZE	6.0*	6.5	7.0	7.5	8.0	8.5	9.0	10.0*
mm	77	83	89	95	102	108	115	120
TEST METHOD					EN 420:2003 + A1:2009			

Glove Cleanliness Characteristics

PARTICLES				TYPICAL PARTICLE COUNT			TEST METHOD	
≥ 0.5µm(counts/cm²)					<1200			IEST-RP-CC005.4
TYPICAL EXTRACTABLE IONS					TEST METHOD			
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.4
(µg/cm ²)	ND	0.12	0.01	ND	0.01	ND	0.01	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(µg/cm ²)	ND	0.01	NT	0.03	0.07	0.02	ND	
ND = Not Detected, NT = Not Tested								

Sterilization

Method: Gamma irradiation Minimum Dose: 25kGy Sterility Assurance Level: 10⁻⁶

Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.





TO ORDER

Re-order code	Size	Packing
BLLS60	6.0*	One pair per inner PE wallet; one wallet per sealed EasyTear PE pouch; 10 pouches
BLLS65	6.5	per sealed outer PE bag; 10 outer bags per lined carton (100 pairs).
BLLS70	7.0	
BLLS75	7.5	*Size subject to minimum order quantity and lead time.
BLLS80	8.0	
BLLS85	8.5	
BLLS90	9.0	
BLLS100	10.0*	

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd

Minton Enterprise Park Oaks Drive Newmarket, Suffolk CB8 7YY United Kingdom

BLLS/1904/PDS40



Caution: This product contains natural rubber latex (latex) which may cause allergic reactions in some users. Safe use of this glove by or on latex sensitized individuals has not been established.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

**Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2018 Ansell Limited. All Rights Reserved.