

### BioClean-C<sup>™</sup> Sleeve Covers BCSC

# Non-sterile cleanroom sleeve covers, for protection against chemotherapy drugs

- Optimized protection: BioClean™
   chemotherapy-protective sleeve covers
   are specially developed to protect
   against a range of chemotherapy drugs,
   with ultrasonically bonded seams and
   protective tape, for added security
- Guaranteed cleanliness: These chemotherapy-protective garments are constructed from CleanTough™ material that is both lightweight and low-linting
- Assured barrier protection: BioClean-C<sup>™</sup> chemotherapy-protective sleeve covers have been tested against ASTM F739-12 permeation standards
- Maximized practicality: These one-sizefits-all sterile sleeve covers are tailored for quick and simple donning
- Secure fit: An integrated thumb loop keeps the sleeve from rolling back and exposing the arm or wrist.

### **Key Features and Benefits**

- Ultrasonically bonded seam: For sleeve covers that offer a secure fit
- Lightweight, low-linting CleanTough™ fabric: Comfort and durability
- ASTM F739-12 compliance: Assured permeation protection



### **Industries**

- Controlled and Critical Environments
- Production and Manufacturing
- Laboratory and Research







## BioClean-C™ Sleeve Covers BCSC

### **TECHNICAL DATA SHEET**

### **PRODUCT INFORMATION**

Material	{EB3FC5C8-9B74-43B1-9DE4-155A75700CB8}
Audit Standards	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
Standards	ASTM F739, CE 0598, EN 13034:2005 + A1:2009, EN 13935-2, EN ISO 14325, Partial Body Protection Only, Category III, EN 14605:2005 + A1:2009, UKCA
Packaging Overview	<ul> <li>30 pieces per sealed inner PE bag; 1 inner bags per sealed outer PE bag; 6 outer bags per lined carton (180 pieces)</li> </ul>
Storage	Keep away from direct sunlight; store in a dry place and keep in the original packaging. Keep away from ozone sources. If products are properly stored, as indicated, they won't lose their performances or change characteristics significantly. If products could be affected by ageing or storage, the expiry date is mentioned on the packaging materials.
Cleanroom Class	Class 10/ISO 4
Shelf Life	5 years
Construction	Ultrasonically bonded seams covered with protective tape
Characteristics	Low particulating

### **PARTICLE SHEDDING TEST RESULTS**

TEST	RESULT	
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <1700	

### **ASTM F739-12 TEST METHOD RESULTS**

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm2 /min
CISPLATIN	>480
CARMUSTINE	>480
CYCLOPHOSHAMIDE	>480
DOXORUBICINHYDROCHLORIDE	>480
5-FLUOROURACIL	>480
METHOTREXATE	>480
ETOPOSIDE	>480
PACLITAXEL	>480
THIOTEPA	>456

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. \*For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

### **SIZE CHART**

BCSC; Size: Universal





### **BioClean-C™ Sleeve Covers BCSC**

#### MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	EN ISO 9073-4	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>80%	2	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H <sub>2</sub> SO <sub>4</sub>	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Seam Strength <sup>1</sup>	>50 N	2	ISO 13935-2

### **ORDERING INFORMATION**

	SIZE	BioClean-C Chemo Sleeve Covers BCSC
BCSC	REORDER NO.	BCSC

### **Performance Standards and Regulatory Compliance**









### For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

### **Asia Pacific Region**

Ansell Global Trading Center T: +603 8310 6688 F: +603 8310 6699

### North America Region

Ansell Healthcare Products LLC US T: +1 800 800 0444 US F: +1 800 800 0445 CA T: +1-800-363-8340

### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. T: +52 442 248 1544 / 248 3133

#### Australia

Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578

Ansell Nitritex T: +44 1638 663338 F: +44 1638 668890



Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.





Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.