


## Sterile, nonwoven polycellulose wipes, providing superior absorption capabilities

- **Enhanced absorbency:** BioClean™ Oryx BOWS cleanroom wipes are composed of hydroentangled polycellulose, delivering outstanding absorption properties
- **Minimized allergy risks:** They feature no whitening agents or optical brighteners, reducing the risk of allergic reactions
- **Guaranteed cleanliness:** These low-linting wipes are sterilized via gamma irradiation and packed in an ISO Class 5 cleanroom facility, ensuring low levels of particulates and extractables, while sampling and inspection are carried out in accordance with ISO 2859-3 standards
- **Heightened robustness:** BioClean™ Oryx BOWS nonwoven wipes also benefit from excellent durability and strength



### Key Features and Benefits

- **Hydroentangled polycellulose design:** Excellent absorption properties
- **No optical brighteners or whitening agents:** Lesser allergy risks
- **ISO Class 5 cleanroom-packed:** Minimal extractable and particulate levels

### Industries

- Controlled and Critical Environments
- Production and Manufacturing



# BioClean™ Oryx BOWS 12

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

Material	Polycellulose
Color	White
Audit Standards	ISO 9001
Standards	ISO 2859, ISO 9001:2015
Packaging Overview	BOWS-12: 10 pieces (C-folded) per sealed inner PE bag; 10 inner PE bags per sealed outer PE bag; 18 outer bags per lined carton (1800 pieces)
Country Of Origin	China
Available Sizes	300mm x 300mm (12" x 12")
Sterilization Method	GAMMA irradiation (25 kGy)
Cut	Blade
Weight	68gsm (±3gsm)
Cleanroom Class	Class 100/ISO Class 5 & EU GMP Grade A/B and other sterile cleanrooms
Shelf Life	Five (5) years from date of manufacture.

### PHYSICAL PROPERTIES

Force at Break (N)	Machine Direction	98
	Cross Direction	42
Absorption	Extrinsic Sorbency Capacity (ml/m <sup>2</sup> )	305.90
	Intrinsic Sorbency Capacity (ml/g)	4.60

Typical Extractable Ions					
	Sodium	Potassium	Magnesium	Calcium	Chloride
(µg/cm <sup>2</sup> )	0.422	0.038	0.116	0.228	0.07

ND = Not Detected, NT = Not Tested

Particle generation (>0.5µm) orbital shake method	4.6 x 10 <sup>3</sup> /cm <sup>2</sup>		
Particle generation Helmke drum method (average counts per minute)	>0.3µm	>0.5µm	>5.0µm
	1261 DRY / 363 WET*	850 DRY / 170 WET*	85 DRY / 29 WET*

### ORDERING INFORMATION

	SIZE	300mm x 300mm (12" x 12")
BOWS 12	REORDER NO.	BOWS-12

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

#### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

#### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

#### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

#### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

#### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

#### U K

Ansell Nitritex  
T: +44 1638 663338  
F: +44 1638 668890

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

