



BioClean-D™ Drop-down Sterile Garment with Hood and Facemask S-BDSH3

Drop-down Garment - Sterile

The BioClean-D™ Drop-down Garment with Hood and Face Mask is a sterile antistatic disposable garment manufactured from low-linting CleanTough material. Its unique design offers true aseptic donning, with internal coloured tabs to indicate safe touch points to prevent touching the outside surface. The innovative up and over donning design eliminates the risk of the garment touching the floor, and strategically placed quick release tabs (to hold and remove during zip closure) ensure aseptic donning through out the donning process.

Please contact Ansell Customer Service for specific chemotherapy drug permeation times and recommendations.

Key Features and Benefits

- Integrated cleanroom face mask consist of 3ply with ties for secure hold
- Elasticated back, hood, cuffs and ankles
- Foot-loop to aid smooth closure of zip
- Thumb loops to ensure a secure hold
- Quick release press stud tabs for aseptic donning
- Low-linting CleanTough material

Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing
- Laboratory and Research





BioClean-D™ Drop-down Sterile Garment with Hood and Facemask S-BDSH3

TECHNICAL DATA SHEET

PRODUCT INFORMATION

Material	CleanTough™
Audit Standards	ISO 14001, Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D, NEBB Certified Cleanrooms
Standards	ASTM F739, ISO 11137-1:2006, EN 1149-5:2008, EN 13934-1, EN 530, EN 6530, EN 7854, EN 863, EN 9073-4, EN ISO 13688:2013
Packaging Overview	One piece per sealed inner PE bag; one inner bag per sealed outer PE bag; 20 outer bags per per lined carton (20 pieces).
Country Of Origin	Sri Lanka
Sterilization Method	GAMMA irradiation (25 kGy)
Sterilization Minimum Dose	25kGy
Sterility Assurance Level	10 ⁻⁶
Cleanroom Class	Class 10/ISO Class 4 & EU GMP Grade A/B and other sterile cleanrooms
Shelf Life	Three (3) years from date of manufacture
Construction	Bound seams with single needle stitching
Characteristics	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

PARTICLE SHEDDING TEST RESULTS

TEST	RESULT
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000

ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm ² /min
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

SIZE CHART

S-BDSH-XS; Size: XS, Chest: 76-84cm (30"-33"), Height: 158-164cm (5'2"-5'4")
S-BDSH-S; Size: S, Chest: 84-92cm (33"-36"), Height: 164-170cm (5'4"-5'6")
S-BDSH-M; Size: M, Chest: 92-100cm (36"-39"), Height: 170-176cm (5'6"-5'9")
S-BDSH-L; Size: L, Chest: 100-108cm (39"-42"), Height: 176-182cm (5'9"-6'0")
S-BDSH-XL; Size: XL, Chest: 108-116cm (42"-45"), Height: 182-188cm (6'0"-6'2")
S-BDSH-XXL; Size: 2XL, Chest: 116-124cm (45"-48"), Height: 188-194cm (6'2"-6'4")
S-BDSH-XXXL; Size: 3XL, Chest: 124-132cm (48"-51"), Height: 194-200cm (6'4"-6'6")
S-BDSH-XXXXL; Size: 4XL, Chest: 132-140cm (51"-54"), Height: 200-206cm (6'6"-6'8")
S-BDSH-5XL; Size: 5XL, Chest: 140-148cm (54"-56"), Height: 206-212cm (6'8"-6'11")
S-BDSH-6XL; Size: 6XL, Chest: 148-156cm (56"-58"), Height: 212-218cm (6'11"-7'2")
S-BDSH-7XL; Size: 7XL, Chest: 156-164cm (61"-64"), Height: 218-224cm (7'2"-7'4")
S-BDSH-8XL; Size: 8XL, Chest: 164-172cm (51"-54"), Height: 224-230cm (7'4"-7'6")



BioClean-D™ Drop-down Sterile Garment with Hood and Facemask S-BDSH3

MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS
Abrasion Resistance	10 to 100 cycles	1
Flex Cracking Resistance	5,000 to 15,000 cycles	3
Puncture Resistance	8 N	1
Trapezoidal Tear Resistance Cross Direction (CD)	CD 29.3 N	2
Trapezoidal Tear Resistance Machine Direction (MD)	MD 55.5 N	3
Tensile Strength Cross Direction (CD)	CD 48 N	1
Tensile Strength Machine Direction (MD)	MD 97 N	2
Repellence to Liquids – 30% H ₂ SO ₄	96.3%	3
Repellence to Liquids – 10% NaOH	97.6%	3
Repellence to Liquids – O-Xylene	95.7%	2
Repellence to Liquids – Butan-1-ol	96.6%	3
Penetration by Liquids – 30% H ₂ SO ₄	0%	3
Penetration by Liquids – 10% NaOH	0%	3
Penetration by Liquids – O-Xylene	0%	3
Penetration by Liquids – Butan-1-ol	0%	3
Seam Strength ²	70 N	2
Electrostatic Charge Half Decay Time, t ₅₀ (secs)	0.07	PASS

1. Seam not destroyed

ORDERING INFORMATION

	SIZE	XS	S	M	L	XL	XXL
S-BDSH3	REORDER NO.	S-BDSH3-XS	S-BDSH3-S	S-BDSH3-M	S-BDSH3-L	S-BDSH3-XL	S-BDSH3-XXL

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV
T: +32 (0) 2 528 74 00
F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center
T: +603 8310 6688
F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC
US T: +1 800 800 0444
US F: +1 800 800 0445
CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.
T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited
T: +61 1800 337 041
F: +61 1800 803 578

UK

Ansell Nitritex
T: +44 1638 663338
F: +44 1638 668890

Performance Standards and Regulatory Compliance



Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

