

Dual-layer, chemical-resistant EMS gloves, offering wearers advanced barrier protection

- Reinforced defenses: MICROFLEX[®] LifeStar EC[™] 93-868 chemical-resistant EMS gloves' dual-layer, dual-color design offers users reinforced barrier protection and chemical resistance
- Specialized protection: These nitrile gloves' layered design also satisfies EN 374 Type B standards for chemical splash protection
- Sustained grip: Textured fingertips and a non-stick/non-foaming composition help medical users and healthcare professionals maintain a strong grip in dry and wet conditions
- Extended protection: These medical gloves' boast an extended cuff over the wrist and lower forearm, protecting workers on the job
- Low AQL: These medical exam gloves' low 0.65 AQL reinforces their barrier integrity



Industries

- Chemical
- Life Sciences
- Food Processing
- Healthcare

Recommended For

- Administering drugs
- Inspection, selecting, checking parts
- Sample taking and processing
- Transferring liquids and solids



TECHNICAL DATA SHEET

	Product Information
External Glove Surface	Textured Fingers
Audit Standards	ISO 13485, ISO 9001
Product Certification	Medical Device Regulation (EU) 2017/745 Class I, Personal Protective Equipment Regulation (EU) 2016/425 Category III risks
Packaging Overview	100 gloves per dispenser 10 dispensers per case 1000 gloves per case XXXL: 90 gloves per dispenser
Storage Instructions	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country Of Origin	Malaysia
Product Segmentation	High Risk
Antistatic	Yes EN1149
Vulcanization Chemical Accelerators	 Zinc Dibutyldithiocarbamate (ZDBC) Only a very small number of users may be sensitive to this ingredient(s) and hence may develop irritant and/or allergic contact reactions.

PHYSICAL PROPERTIES

	Typical	Testing Method	
Length (mm/inches)	≥ 280 / 11.0		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	0.65 AQL		ASTM D5151,EN 374-2
Palm Thickness (mm/mils)	0.15 / 5.5		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.22 / 8.7		ASTM D3767,EN 420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	27	22	ASTM D412 & D573
Elongation at Break (%)	650	550	ASTM D412
Force at break (N)	14	11	EN 455-2

ORDERING INFORMATION

Size	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)	XXL (10.5 - 11)	XXXL (11.5 - 12)
Product Code	93868070	93868080	93868090	93868100	93868110	93868120

Performance Standards and Regulatory Compliance



For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Asia Pacific Region MY +603 8310 6688 apac.medical@ansell.com CN: +86 21 38275000

infochir JP: +813 5549 8151 al.jp@ansell.com info.m

North America Region Ansell Healthcare Products LLC T: +1 800 800 0444 F: +1 800 800 0445

Latin America & Caribbean Region BR +55 (11) 3356-3100 latam.medical@ansell.com MX: +52 442 296 2050 latam.medical@ansell. CO: +57 1 288 3247 latam.medical@ansell. ell.com

Australia Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578

Russia Ansell PYC Ten. +7 495 258 13 16

Ansell, [®] and [™] are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking © 2024 Ansell Limited. All Rights Reserved.

ell.com

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

