




## BioClean™ Isopure Plus S BIWP 12

# Sterile, polyester, cleanroom wipes featuring ultrasonically sealed edges, for minimal particulate contamination

**Dimensions:** 305mm x 305mm/12" x 12"

- **Enhanced performance:** BioClean™ Isopure Plus S BIWP 12 sterile wipes are manufactured from 100% continuous-filament polyester, for highly durable cleanroom wipes that ensure superior absorption
- **Added protection:** These low-linting sterile wipes feature ultrasonically sealed edges, for a reduced risk of particulates entering the controlled environment
- **Assured sterility:** BioClean™ Isopure Plus S BIWP 12 cleanroom wipes are sterilized through a gamma irradiation process, making them cleanroom environment-compatible



### Key Features and Benefits

- **Continuous-filament polyester:** Excellent absorption performance
- **Ultrasonically sealed edges:** Lesser risk of particulate contamination
- **Gamma irradiation sterilization:** Cleanroom environment compatibility

### Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Laboratory and Research



# BioClean™ Isopure Plus S BIWP 12

## TECHNICAL DATA SHEET

### PRODUCT INFORMATION

Material	Polyester / Polyurethane
Color	White
Audit Standards	ISO 9001:2015
Standards	EN 420:2003 + A1:2009, ISO 2859, ISO 9001:2015
Packaging Overview	100 pieces per sealed inner PE bag; one inner PE bag per sealed outer PE bag; 10 outer bags per lined carton (1000 pieces)
Country Of Origin	Malaysia
Available Sizes	230mm x 230mm (9" x 9")
Sterilization Method	Gamma Irradiation
Cut	Ultrasonic
Weight	130gsm (±5gsm)
Cleanroom Class	Class 10/ISO Class 4 & EU GMP Grade A/B and other sterile cleanrooms
Shelf Life	Three (3) years from date of manufacture.

### PHYSICAL PROPERTIES

Force at Break (N)	Machine Direction	3.83 N / 68%
	Cross Direction	4.92 N / 239%
Absorption	Extrinsic Sorbency Capacity (ml/m <sup>2</sup> )	370
	Intrinsic Sorbency Capacity (ml/g)	2.15

Typical Extractable Ions					
	Sodium	Potassium	Magnesium	Calcium	Chloride
(µg/cm <sup>2</sup> )	0.0081	ND	ND	ND	0.002

ND = Not Detected, NT = Not Tested

Particle generation (≥0.5µm) orbital shake method	710		
Particle generation Helmke drum method (average counts per minute)	≥0.3µm	≥0.5µm	≥5.0µm
	1750	884	64

### ORDERING INFORMATION

	SIZE	300mm x 300mm (12" x 12")
S BIWP 12	REORDER NO.	S BIWP 12

For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

#### Europe, Middle East & Africa Region

Ansell Healthcare Europe NV  
T: +32 (0) 2 528 74 00  
F: +32 (0) 2 528 74 01

#### Asia Pacific Region

Ansell Global Trading Center  
T: +603 8310 6688  
F: +603 8310 6699

#### North America Region

Ansell Healthcare Products LLC  
US T: +1 800 800 0444  
US F: +1 800 800 0445  
CA T: +1-800-363-8340

#### Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V.  
T: +52 442 248 1544 / 248 3133

#### Australia

Ansell Limited  
T: +61 1800 337 041  
F: +61 1800 803 578

#### UK

Ansell Nitritex  
T: +44 1638 663338  
F: +44 1638 668890

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2024 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

