

BioClean-D™ Sterile Kit S BDHB

Sterile cleanroom coverall with hood and overboots, for head-to-toe protection

- Reduced contamination risks: The BioClean-D Sterile Kit S BDHB features CleanTough™ material, for lightweight, low-linting coveralls that offer good barrier protection and are less susceptible to contamination, making them ideal for cleanroom use
- Added features: This sterile coverall kit features an integrated hood and separate overboots, for enhanced allround personal protection, while slipresistant soles prevent workplace injuries
- Optimized packaging: All garments are provided in a single package, making them more convenient and reducing overall packaging waste
- Enhanced fit: The BioClean™ coverall is equipped with a front zip with a protective flap, elasticated back, cuffs and ankles, as well as thumb loops to provide wearers with a more secure and comfortable fit



Key Features and Benefits

- CleanTough™ material: For a lightweight, low-linting sterile coverall
- Integrated hood and separate overboots: Comprehensive coverage
- Single kit for all garments: Convenient handling, less packaging waste

Industries

- Controlled and Critical Environments
- Production and Manufacturing
- Pharmaceutical Manufacturing
- Biotechnology Manufacturing
- Medical Device Manufacturing





BioClean-D™ Sterile Kit S BDHB

TECHNICAL DATA SHEET

PRODUCT INFORMATION

Material	CleanTough™
Color	White
Audit Standards	Manufacturing QMS Audit Standards ISO 9001, PPE Regulation 2016 425 Module D
Standards	ASTM F739, EN ISO 13688:2013, EN 13935-2, EN 1149-5:2018, Category III, EN ISO 13982-1:2004 + A1:2010, EN 13034:2005 + A1:2009
	One coverall with hood and one pair of overboots per sealed inner bag; one inner bag per sealed outer PE kit bag; 20 kits per lined carton, and only for size 3XL 15 kits per lined carton
Packaging Overview	*More sustainable packaging: Packed in recyclable plastic packaging and delivered in recycled cardboard shipper cases. Inner and outer bags and liner are made from polyethylene (PE) based film. Always check your local recyclable status as these materials may not be considered suitable for recycling in your location.
Storage	Keep away from direct sunlight; store in a dry place and keep in the original packaging. Keep away from ozone sources. If products are properly stored, as indicated, they won't lose their performances or change characteristics significantly. If products could be affected by ageing or storage, the expiry date is mentioned on the packaging materials.
Country Of Origin	Malaysia
Sterilization Method	GAMMA irradiation (25 kGy)
Sterilization Minimum Dose	25kGy
Sterility Assurance Level	10 ⁻⁶
Cleanroom Class	Class 10/ISO 4 & EU GMP Grade A
Shelf Life	Three (3) years from date of manufacture.
Construction	Bound seams with single needle stitching
Characteristics	*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, and so are ideal for use in a static-safe environment.

PARTICLE SHEDDING TEST RESULTS

TEST	RESULT	
Particle Shedding (Helmke Drum Test)	≥ 0.5Qm (counts/min) <2000	

ASTM F739-12 TEST METHOD RESULTS

DRUG	Mean Breakthrough Time (MBT), Minutes Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 Qg/cm² /min
CISPLATIN	>240
CARMUSTINE	<6
CYCLOPHOSHAMIDE	217 (275,162,215)
DOXORUBICINHYDROCHLORIDE	>240
5-FLUOROURACIL	>240
METHOTREXATE	>240
ETOPOSIDE	>240
PACLITAXEL	<10
THIOTEPA	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory. *For Bioclean D and Bioclean 2000, the chemical permeation results relates to the fabric performance for reference only. Seams and closures may have lower breakthrough times. We recommend garments with sealed seams such as Bioclean-C to be worn over the coverall for added protection against chemotherapy drugs handling.

SIZE CHART

S-BDHB-S; Size: S, Chest: 84-92cm (33"-36"), Height: 164-170cm (5'4"-5'6")

S-BDHB-M; Size: M, Chest: 92-100cm (36"-39"), Height 170-176cm (5'6"-5'9") S-BDHB-L; Size: L, Chest: 100-108cm (39"-42"), Height: 176-182cm (5'9"-6'0")

S-BDHB-XL; Size: XL, Chest: 108-116cm (42"-46"), Height: 182-188cm (6'0"-6'2")

S-BDHB-2XL; Size: 2XL, Chest: 116-124cm (46"-49"), Height: 188-194cm (6'2"-6'4") S-BDHB-3XL; Size: 3XL, Chest: 124-132cm (49"-52"), Height: 194-200cm (6'4"-6'6")





BioClean-D™ Sterile Kit S BDHB

MATERIAL PERFORMANCE TEST RESULTS

TEST	RESULT	PERFORMANCE CLASS	PERFORMANCE STANDARD
Abrasion Resistance	>10 cycles	1	EN 12947-2
Flex Cracking Resistance	>50,000 cycles	6	EN ISO 7854
Puncture Resistance	>5 N	1	ISO 13996
Trapezoidal Tear Resistance Cross Direction (CD)	>10 N	1	EN ISO 9073-4
Trapezoidal Tear Resistance Machine Direction (MD)	>10 N	1	EN ISO 9073-4
Tensile Strength Cross Direction (CD)	>30 N	1	EN ISO 13934-1
Tensile Strength Machine Direction (MD)	>30 N	1	EN ISO 13934-1
Repellence to Liquids - 30% H ₂ SO ₄	>90%	3	ISO 6530
Repellence to Liquids - 10% NaOH	>90%	3	ISO 6530
Repellence to Liquids - O-Xylene	>80%	2	ISO 6530
Repellence to Liquids - Butan-1-ol	>90%	3	ISO 6530
Penetration by Liquids - 30% H ₂ SO ₄	<1%	3	ISO 6530
Penetration by Liquids - 10% NaOH	<1%	3	ISO 6530
Penetration by Liquids - O-Xylene	<1%	3	ISO 6530
Penetration by Liquids - Butan-1-ol	<1%	3	ISO 6530
Inward leakage of aerosols of fine particles ¹	PASS	N/A	EN ISO 13982-2
Resistance to penetration by spray (Spray Test) ¹	PASS	N/A	EN ISO 17491-4
Seam Strength ²	>50 N	2	ISO 13935-2
Electrostatic Charge Half Decay Time, t ₅₀ (secs)	PASS	N/A	EN1149-3

^{1.} All interfaces with additional PPE were taped during testing, as required by the standards.

ORDERING INFORMATION

	SIZE	BioClean-D Sterile Anti-Static Kit	BioClean-D Sterile Anti-Static Kit
S BDHB	REORDER NO.	S-BDHB-S, S-BDHB-M, S- BDHB-L, S-BDHB-XL, S- BDHB-2XL	S-BDHB-3XL

For additional information visit us at www.ansell.com, or call us at

Europe, Middle East & Africa Region

Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01

Asia Pacific Region

Ansell Global Trading Center T: +603 8310 6688 F: +603 8310 6699

North America Region

Ansell Healthcare Products LLC US T: +1 800 800 0444 US F: +1 800 800 0445 CA T: +1-800-363-8340

Latin America & Caribbean Region

Ansell Commercial Mexico S.A. de C.V. T: +52 442 248 1544 / 248 3133

Australia

Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578

UK

Ansell Nitritex T: +44 1638 663338 F: +44 1638 668890 Performance Standards and Regulatory Compliance








Ansell, @ and $^{\text{M}}$ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending: www.ansell.com/patentmarking @ 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.





^{2.} Seam not destroyed., 3. The material is static dissipative. Tested in accordance with EN1149-5